

## XRF 分析比較

		天山石	庵治石
		wt. %	wt. %
1	SiO <sub>2</sub>	66.681	69.41
2	Al <sub>2</sub> O <sub>3</sub>	17.143	14.84
3	CaO	4.6323	3.09
4	Fe <sub>2</sub> O <sub>3</sub>	3.7631	2.56 (FeO)
5	Na <sub>2</sub> O	3.4535	3.75
6	K <sub>2</sub> O	2.1963	2.54
7	MgO	1.1094	0.74
8	TiO <sub>2</sub>	0.4127	0.38
9	P <sub>2</sub> O <sub>5</sub>	0.26203	0.10
10	MnO	0.07926	0.06
11	SrO	0.060890	
12	ZrO <sub>2</sub>	0.055553	
13	BaO	0.054807	
14	Co <sub>3</sub> O <sub>4</sub>	0.043005	
15	CuO	0.026035	
16	S <sub>2</sub> O <sub>3</sub>	0.010625	
17	ZnO	0.010242	
18	Rb <sub>2</sub> O	0.0056215	
19	Cl	ND	